



**Product Data Sheet &  
General Processing Conditions**

**ZOVGOV® M23GB6  
Acetal (POM)  
Glass Bead**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	30 %	30 %	
Specific Gravity	1.62	1.62	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0140 - 0.0220 in/in	1.40 - 2.20 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.6 ft-lbs/in	35 J/m	D 256
unnotched 1/8 in (3.2 mm) section	6.0 ft-lbs/in	320 J/m	D 4812
Tensile Strength	5700 psi	39 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.55 x 10 <sup>6</sup> psi	3792 MPa	D 638
Flexural Strength	10000 psi	69 MPa	D 790
Flexural Modulus	0.48 x 10 <sup>6</sup> psi	3310 MPa	D 790

**THERMAL**

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per MOLAN Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	360 - 425 °F	182 - 218 °C
Mold Temperature	175 - 225 °F	79 - 107 °C
Drying	2 hrs @ 250 °F	2 hrs @ 121 °C
Moisture Content	0.15 %	0.15 %
Dew Point	-25 °F	-32 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.